

KEMPERDUR AC filler



Uses

- Quartz sand mixture to produce a coating consisting of KEMPERDUR AC coating or KEMPERDUR AC Park

Characteristics

- Graded grading curve
- System-tested and matched to the application purpose

Pack sizes

23 kg in paper bag

Usage guide

as KEMPERDUR AC coating:

min. 4.0 kg/m² (2.8 kg KEMPERDUR AC filler) KEMPERDUR AC coating at a layer thickness of 3 mm.

KEMPERDUR AC Coating System working packs consist of:

- 10.0 kg KEMPERDUR AC coating as component A
- KEMPEROL CP catalyst powder acc. to Table as a component B
- 23 kg KEMPERDUR AC filler as Component C.

as KEMPERDUR AC Park:

at least 4.0 kg/m² (2.8 kg KEMPERDUR AC filler)

Working packings of the coating consist of:

- 10.0 kg KEMPERDUR AC Park as component A
- KEMPEROL CP catalyst powder acc. to Table as a component B
- 23 kg KEMPERDUR AC filler as component C.

Shelf Life

Keep cool and dry. The bags must be kept air-tight.

Properties

Form	Granular /solid
------	-----------------

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Application

Work steps after preparation of the substrate:

- Mixing in of KEMPEROL CP catalyst powder in KEMPERDUR AC coating
- Mixing in of KEMPERDUR AC filler

Mixing must be carried out with a slow-running mixing device (preferably a positive mixer) until you achieve a homogeneous mixture.

PPE

For application in enclosed areas ensure there is sufficient ventilation. Always wear personal protective equipment (breathing equipment with filter A/P2, protective gloves, safety goggles).

Important notes

The safety data sheets, the labeling of the containers, the hazard warnings and the safety instructions on the containers must be observed during transport, storage and processing.

Disposal

Dispose of in accordance with the official regulations. Further information on disposal can be found in the respective safety data sheets, Section 13.

General information

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is there-

fore essential that you always have the latest data sheet to hand. The latest version can be downloaded from kemperol.de under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application technology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery.

Issued: Vellmar, 2025-02-17