

KEMPEROL 2K-PUR Speedshot



Uses

- To accelerate the reaction of KEMPEROL 2K-PUR Sealing

Characteristics

- Shortens the setting process of KEMPEROL 2K-PUR Sealing

Pack sizes

0,9 kg in a plastic bottle with a measuring chamber

Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

Usage guide

The data refer to a quantity of 1 kg KEMPEROL 2K-PUR Sealing

Temperature*** [°C]		10 ml	20 ml	30 ml
5°C	V*	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V*	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h

Temperature*** [°C]		10 ml	20 ml	30 ml
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

* Working time

** Further coating after

*** Temperature of KEMPEROL 2K-PUR Sealing

The data refer to a quantity of 2.5 kg KEMPEROL 2K-PUR Sealing

Temperature*** [°C]		1 Shot (25 ml)	2 Shot (50 ml)	3 Shot (75 ml)
5°C	V*	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V*	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

* Working time

** Further coating after

*** Temperature of KEMPEROL 2K-PUR Sealing

The data refer to a quantity of 12.5 kg KEMPEROL 2K-PUR Sealing

Temperature*** [°C]		1 Shot (25 ml)	2 Shot (50 ml)	3 Shot (75 ml)
5°C	V*	-	-	22 min
	W**	-	-	4.5 h
10°C	V*	-	-	22 min
	W**	-	-	4.5 h
20°C	V*	20 min	18 min	-
	W**	7 h	6 h	-

* Working time

** Further coating after

*** Temperature of KEMPEROL 2K-PUR Sealing

Properties

Form Liquid

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Application

Preparation

To add the correct dosage of KEMPEROL 2K-PUR Speedshot first screw the blue cap to the measuring chamber of the bottle. Then squeeze the bottle repeatedly until the dosage chamber has filled up to the 25ml line. 25 ml is one shot.

If the ambient temperature is 10°C or lower, it is recommended that you store and mix the components at room temperature.

Sachet

KEMPEROL 2K-PUR Sealing mix in the kneading bag according to instructions, and then transfer. KEMPEROL 2K-PUR Speedshot mix with stirring rod or slow-running stirrer, streak-free into the finished sealant. Mixing time approx. 1 minute.

PPE

Personal protective equipment should be worn. We recommend a hand protection and skin protection plan adapted to the workplace. Clean the tools immediately after use with KEMCO MEK Cleaning Agent.

Important notes

The safety data sheets, the labeling of the containers, the hazard warnings and the safety instructions on the containers must be observed during transport, storage and processing. The BG-Chemie data sheets must be observed during processing.

Do not allow to enter waters, drains or to penetrate the ground.

Disposal

liquid	EAK 08 04 09
--------	--------------

General information

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and application instructions reflect the current level of knowledge in our company and the experience with our products. In each case, the new edition supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practise. The latest version can be retrieved from the KEMPER SYSTEM Login section. When using our products, a detailed, object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults, and this only if our relevant product has been used and applied according to

the instructions in our technical data sheets. Correct application of our products therefore falls entirely within the scope of liability and responsibility of the user (contractor). Our products are sold exclusively on the bases of our conditions of sale and delivery.

Issued: Vellmar, 2023-03-30