

## KEMPERTEC AC Primer



### Uses

- As a primer and for a force-fit, permanent bond between substrate and
  - KEMPEROL AC Speed
  - KEMPERDUR AC Park and KEMPERDUR AC Park+
  - KEMPERTEC AC GF Gradient filler and KEMPERTEC AC RM Repair Mortar
  - KEMPEROL V 210 M and KEMPEROL BR M
- As alkaline protection layer
- For new buildings and repair work
- As bonding agent for trowel-applied filler and repair mortar
- Use as primer according to BASt (H PMMA:2018), e.g.: Bridge supporting structure

### Characteristics

- Fast hardening
- Solvent-free
- Good adhesion
- Environmentally declared according to valid international standards (EPD)
- 2-component
- Processable down to -5 °C ambient temperature
- Resin base: PMMA

### Pack sizes

20 kg (blue-transparent) containers (component A) in combination with KEMPEROL CP catalyst powder (component B), quantity added - see Table

### Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

### Usage guide

Depending on the absorbency of the substrate:

As priming: at least 0.5 kg/m<sup>2</sup>

As alkali protection: at least 0.4 kg/m<sup>2</sup>

Usage must not exceed 0,75 g/m<sup>2</sup>, otherwise bulging and flaking can occur!

### Properties

Form	Comp. A liquid
	Comp. B powder
Standard colour	transparent blue
	blue-transparent
	Transparent
Workability time *	approx. 11 min
(2% KEMPEROL CP catalyst powder)	
Rainproof after *	approx. 30 min
Can be walked on after *	approx. 30 min
Further coating after*	approx. 30 min

\* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

### Curing

Hardening takes place with KEMPEROL CP catalyst powder. The quantity added depends on the temperature.

Temperature [°C]	KEMP. CP cat. powder - quantity [20 g bag] for 1 kg	KEMP. CP cat. powder - quantity [100 g bag] for 5 kg	KEMP. CP cat. powder - quantity [100 g bag] for 20 kg	Pot life in container [min]	Surface cured [min]
-5 °C	2 bags	2 bags	8 bags	40 min	60 min
0 °C	2 bags	2 bags	8 bags	30 min	50 min
+5 °C	2 bags	2 bags	8 bags	20 min	45 min
+10 °C	2 bags	2 bags	8 bags	18 min	30 min
+20 °C	1 bag	1 bag	4 bags	15 min	30 min
+30 °C	1/2 bag	1/2 bag	2 bags	10 min	15 min

### CE marking

Component to	ETA 03/0025
	ETA 03/0026
	ETA 03/0043
	ETA 03/0044

## Application

---

### Preparing the substrate

Substrates must be dry (residual moisture in concrete in the upper 2 cm < 5%), capable of withstanding loads and free from materials that may hinder adhesion, and must be appropriately prepared.

(refer to Technical Information TI 21 - Substrate Assessment)

The priming recommendations should be followed.

Do not apply during rising temperatures.

Please refer to the Technical Information TI 33 – Working at temperatures below +5°C.

When executed, the surface temperature must be 3 K above the dew point. If the dew point is undershot, a moisture film, which has a separating effect, can form on the surface to be processed (see Technical Information TI 16).

KEMPERTEC AC-Primer may only with KEMPEROL CP catalyst powder may be used. The quantity of the catalyst powder must be adapted to the respective material temperature (see Table Hardening

KEMPEROL CP catalyst powder component B to be mixed thoroughly into KEMPERTEC AC-Primer component A.

### Use as a primer

The KEMPERTEC AC-Primer must be immediately processed, after mixing with KEMPEROL CP catalyst powder poured on the surface and evenly distributed. Prime evenly in one operation with a nylon roller or a rubber slider until saturation. When using a rubber slider, it is necessary to roll over the surface again with the perlon roller to avoid material accumulation. The next stage can be started after approx. 30 minutes when the primer surface is no longer tacky.

### Use as a filling compound

Before applying the filling compound, apply KEMPERTEC AC-Primer.

To compensate any irregularities in the horizontal between 2 and 6 mm, the KEMPERTEC AC-Primer is mixed with KEMPERTEC KR Quartz Sand Mixture in a ratio of approx. 1: 3 and applied to the prepared and primed substrate.

### Use as a repair mortar

Before applying repair mortar, apply KEMPERTEC AC-Primer.

To level out unevenness, blowholes and small break-outs in the horizontal plane up to 20 mm deep, the KEMPERTEC AC-Primer shall be mixed with the KEM-

PERTEC KR Quartz Sand Mixture in a ratio of approx. 1:8. Note that when applying layer thicknesses of more than approx. 2 cm intense heat generation occurs.

This ratio may be varied depending on the particular application and the ambient conditions.

### Use as an protective alkaline layer / bonding coat

To protect KEMPEROL waterproofing systems against alkaline media (Technical Information TI 15 - Alkalinity) or to create a bonding coat apply a coat of KEMPERTEC AC Primer (consumption min. 0.4 kg/m<sup>2</sup>).

The still fresh coat must be spread with KEMCO NQ 0712 Natural Quartz a full covering layer (consumption at least 1.5 kg/m<sup>2</sup>).

### Use as a primer on the bridge support structure

In order to use the primer in a coating system on bridges the instructions for use are binding.

### Work interruption and further coating

Operations must be completed within the next 8 days, otherwise separation effects may occur. To avoid this separation effect, it is recommended to sand the still fresh KEMPERTEC AC-Primer with KEMCO NQ 0408 Natural Quartz (approx. 2 kg/m<sup>2</sup>). Otherwise adhesion of subsequent coats cannot be guaranteed and repriming will be necessary.

### PPE

Sufficient ventilation is required. The corresponding instructions should be followed. Always wear personal protective equipment (breathing equipment with filter A/P2, protective gloves, safety goggles). We recommend a hand protection and skin protection plan adapted to the workplace. Clean the tools immediately after use with KEMCO MEK Cleaning Agent.

### Note

---

Observe the following Technical Information:

- TI 21 - substrate preparation
- TI 22 - Application of KEMPEROL/KEMPERDUR AC products
- TI 33 - Processing of / AC Speed+ Sealing at temperatures below +5°C

### Important notes

---

Flammable vapour/air mixtures may form in areas with inadequate ventilation.

The safety data sheets, the labeling of the containers, the hazard warnings and the safety instructions on the containers must be observed during transport, storage and processing. The BG-Chemie data sheets must be observed during processing.

Do not allow to enter waters, drains or to penetrate the ground.

---

## **Disposal**

Dispose of in accordance with the official regulations. Further information on disposal can be found in the respective safety data sheets, Section 13.

---

## **GISCODE**

RMA10

---

## **General information**

The times given above are reduced with higher and increased with lower ambient and substrate temperatures.

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is therefore essential that you always have the latest data sheet to hand. The latest version can be downloaded from [kemperol.de](http://kemperol.de) under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application technology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery.

Issued: Vellmar, 2025-02-19