

KEMPEROL 120 fleece

Uses

- For new buildings and repair work
- Reinforcement for KEMPEROL waterproofing
- For use in the regeneration layer

Characteristics

- System-tested and matched to the application purpose
- Regulates the layer thickness
- Good adaptability
- Base: Polyester

Shelf Life

Keep away from dampness, store dry, flat and crease-free.

Pack sizes

Rolls

Length in metres: 50

Width in cm: 105 / 70 / 52.5 / 35 / 26.25 / 21

Consumption

Consumption of waterproofing when used with KEMPEROL 120 Fleece

Waterproofing	Consumption	Layer thickness
KEMPEROL 2K-PUR	min. 1,6 kg/m ²	approx. 1,4 mm
KEMPEROL 1K-PUR	min. 2,5 kg/m ²	approx. 1,2 mm
KEMPEROL 1K-SF	min. 2,4 kg/m ²	approx. 1,6 mm
KEMPEROL AC Speed	min. 2,2 kg/m ²	approx. 1,7 mm
KEMPEROL AC Speed ⁺	min. 2,2 kg/m ²	approx. 1,9 mm
KEMPEROL PU Aqua	min. 3,0 kg/m ²	approx. 1,4 mm
KEMPEROL LF	min. 2,4 kg/m ²	approx. 1,8 mm

Normative specifications from the relevant waterproofing standards must be observed and complied with.

Properties

Form	solid
Colour	White
Weight [g/m ²]	approx. 120

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

CE marking

Component to	ETA 03/0043
	ETA 12/0416
	ETA 03/0044

Application

Use

Apply approx. 2/3 of KEMPEROL sealant to the prepared and pre-treated substrate, immediately lay in KEMPEROL 120 Fleece without wrinkles or bubbles and press on. Lay the individual non-woven fabric sheets with an overlap of at least 5 cm. Further fresh-in-fresh with approx. 1/3 KEMPEROL sealant soak the inserted KEMPEROL 120 Fleece completely until saturation, avoid excess material.

Connections to door and window elements etc. with a height of <15 cm (from upper edge of coating) should have at least 5 cm of overlap. Connections and joints to third party products have to be produced with an overlap of at least 10 cm.

Disposal

Dispose of in accordance with the official regulations. Further information on disposal can be found in the respective safety data sheets, Section 13.

General information

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is therefore essential that you always have the latest data sheet to hand. The latest version can be downloaded from kemperol.de under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application technology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery.

Issued: Vellmar, 2025-02-17